5

DIFFUSION BARRIER LAYERS AND METHODS OF FORMING SAME Abstract of the Disclosure

A method for use in the fabrication of integrated circuits includes providing a substrate assembly having a surface and forming a barrier layer over at least a portion of the surface. The barrier layer is formed of a platinum(x):ruthenium(1-x) alloy, where x is in the range of about 0.60 to about 0.995; preferably, x is in the range of about 0.90 to about 0.98. The barrier layer may be formed by chemical vapor deposition and the portion of the surface upon which the barrier layer is formed may be a silicon containing surface. The method is used in formation of capacitors, storage cells, contact liners, etc.

EXPRESS MAIL MAILING LABEL NUMBER EL776 904416 US

DATE OF DEPOSIT: 29 AUGUST 2001
I HEREBY CERTIFY THAT THIS PAPER OR FEE IS BEING DEPOSITED WITH THE UNITED STATES POSTAL SRVICE "EXPRESS MAIL POST OFFICE TO ADDRESSEE" SERVICE UNDER 37 CFR 1.10 ON THE DATE INDICATED ABOVE AND IS ADDRESSED TO THE ASSISTANT COMMISSIONER FOR PATENTS.

WASHINGTON D.C. 20231

PRINTED NAME JACQUELYN K. TOPBORG
SKINATURE Jacquelyn K. Torborg